This listing of claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims:

Claim 1 (currently amended): A process for the production of <u>homogeneously packed</u> opal-like or inverse opal-like sphere-based crystals comprising:

- (a) adding a <u>sufficient amount of a water</u> suspension of monospheres <u>having a</u> <u>particle size of 20 nanometers to 30 microns</u> to a flat moving bed <u>porous</u> filtration membrane <u>so as to form a layer thickness on the flat moving bed of 50 microns to 5 mm;</u>
- (b) moving the monospheres on the moving bed filtration membrane <u>substantially</u> <u>horizontally</u> over a vacuum filtration zone, to apply and applying a sufficient substantially <u>constant</u> vacuum filtration pressure to the monospheres to obtain <u>crystalline</u> <u>homogeneously</u> packed monospheres;
- (c) processing the packed monospheres for stabilization, said processing comprising heating and/or chemically bonding the <u>crystalline</u> packed monospheres.

Claim 2 (previously presented): A process according to claim 1, wherein processing of the packed monospheres for stabilization comprises infiltrating the packed monospheres with a chemical bonding agent.

Claim 3 (previously presented): A process according to claim 2, wherein the infiltrating step is accomplished while the packed monospheres are moving on the vacuum bed filtration membrane and while a vacuum filtration pressure is being applied to the packed monospheres.

Claim 4 (previously presented): A process according to claim 2, further comprising

curing the chemical bonding agent.

Claim 5 (previously presented): A process according to claim 1, wherein the monospheres comprise SiO₂.

Claim 6 (previously presented): A process according to claim 1, wherein the monospheres comprise a polymeric material.

Claim 7 (currently amended): A process according to claim 1, for the production of inverse opal-like sphere based crystals comprising: wherein

- (a) adding monospheres to the moving bed filtration membrane;
- (b) moving the monospheres on the moving bed filtration membrane horizontally over a vacuum filtration zone to apply vacuum filtration pressure to the monospheres to obtain packed monospheres;
- (c) processing in step (c) the packed monospheres are processed for stabilization by infiltrating the packed monospheres with a bonding agent; and <u>further comprising</u>
- (d) removing the monospheric material to obtain an inverse opal-like structure comprising air-spheres.

Claim 8 (previously presented): A method according to claim 7, wherein the infiltrating step is accomplished while the packed monospheres are moving on the vacuum bed filtration membrane and while a vacuum filtration pressure is being applied to the packed monospheres.

Claim 9 (previously presented): A process according to claim 7, wherein the bonding agent comprises SiO₂, Al₂O₃, TiO₂, SnO₂, Fe₂O₃, ZrO₂, CeO₂ or Y₂O₃.

Claim 10 (previously presented): A process according to claim 6, wherein the polymeric material comprises polystyrene, polymethacrylate, or polyvinyltoluene.

Claim 11 (previously presented): A process according to claim 1, wherein the suspension has a concentration of monospheres of 2-50% by weight of solids in water.

Claim 12 (previously presented): A process according to claim 11, wherein the concentration is 10% to 20% by weight.

Claim 13 (currently amended): A process according to claim 1, wherein the vacuum pressure is -400 to -600 nm about 400 to about 600 mm Hg.

Claim 14 (currently amended): A process according to claim 11, wherein the vacuum pressure is ~400 to ~600 nm about 400 to about 600 mm Hg.

Claim 15 (currently amended): A process according to claim 12, wherein the vacuum pressure is ~400 to ~600 nm about 400 to about 600 mm Hg.

Claim 16 (currently amended): A process according to claim 1, wherein the monospheres have a particle size in the range of $20 \ \underline{100}$ nanometers to $30 \ \underline{10}$ microns.

Claim 17 (currently amended): A process according to claim 14, wherein the monospheres have a particle size in the range of 20 150 - 450 nanometers to 30 microns.

Claim 18 (currently amended): A process according to claim 1, wherein the monospheres are deposited in a layer thickness of about 50 200 microns to 5 millimeters 1 millimeter.

Claim 19 (currently amended): A process according to claim 1 16, wherein monospheres are deposited in a layer thickness of about 200 microns to 1 millimeter.

Claim 20 (currently amended): A process according to claim 18 17, wherein monospheres are deposited in a layer thickness of about 200 microns to 1 millimeter.

Claim 21 (new): A process according to claim 1, wherein the pores of the porous filtration membrane is equal to or slightly smaller than the spheres to be filtered.